

CoCr28Mo6

ASTM F75 / 2.4979

MATERIAL DATA SHEET

MATERIAL DATA SHEET

CoCr28Mo6

ASTM F75 / 2.4979

MATERIAL

CoCr according to ASTM F75 combines good corrosion and wear resistance. Together with the high biocompatibility, CoCr is one of the most commonly used alloys in medical and dental applications such as prosthetic implants (hip joints, knee implants). Its high-temperature resistance unlocks applications in the energy business including vanes, blades, and nozzles in industrial gas turbines.

CHEMICAL COMPOSITION

ASTM F75 ¹															
	Co	Cr	Mo	Mn	Si	Fe	Ni	C	N	W	Al	Ti	P	B	S
Min.		27.00	5.00												
Max.	Bal.	30.00	7.00	1.00	1.00	0.75	0.50	0.35	0.25	0.20	0.10	0.10	0.02	0.01	0.01

POWDER PROPERTIES

Particle Size ¹	10 - 45 μm
Mass Density ²	$\approx 8.47 \text{ g/cm}^3$
Particle Shape ³	Spherical

MATERIAL DATA SHEET

CoCr28Mo6


ASTM F75 / 2.4979

SLM® PARAMETERS

It only takes 3 tools to make you successful with metal additive manufacturing:

1. The **SLM® machine** fitting your needs,
2. The **metal powder** that defines the later purpose and functionality of a part,
3. Precisely engineered **SLM® parameters** as the missing link.

Our open parameters are the result of our vast experience in multi-laser technology and a diligent development and qualification procedure. They are key to produce fully functional parts with properties you can expect and rely on – whether you are new to AM or a large-scale production operator. We offer them in three categories to you: from high-resolution complex details (**Precision**) up to the highest build rates (**Productivity**) or right in between (**Prime**).



MATERIAL QUALIFICATION

As one of the inventors of the selective laser melting process, we impose the most comprehensive test procedures on ourselves: hundreds of samples, multiple systems, various powder batches, numerous heat-treatments, machined vs. near-net-shape tensile specimens, several surface roughness conditions and angles, fatigue behavior, corrosion investigation, creep testing... Did we miss anything? Get in touch with us!

MATERIAL DATA SHEET

CoCr28Mo6

ASTM F75 / 2.4979

PRECISION

Parameter Set	CoCr28Mo6_PREC_MBP3_V1.0 (20 µm, 400 W)
Validated Data Preparation	Materialise SLM Build Processor
Theoretical Build Rate ⁴	7.4 cm ³ /h
Minimum Relative Density ⁵	99.9 %

Mechanical Properties⁶

M: Mean | SD: Standard deviation

Non-heat-treated (NHT)

Machined	Tensile strength R _m [MPa]		Yield strength R _{p0.2} [MPa]		Elongation at break A [%]	
	M	SD	M	SD	M	SD
Horizontal	1310	35	920	55	15	2
Vertical	1150	15	645	10	30	3

Hardness⁷

M: Mean | SD: Standard Deviation

NHT	Vickers hardness HV10	
	M	SD
	400	5

Surface Roughness⁸

M: Mean | SD: Standard Deviation

	Roughness average Ra [µm]		Mean roughness depth Rz [µm]	
	M	SD	M	SD
As built	14	2	85	10
Corundum	6	1	39	4
Corundum + Glass bead	6	1	41	6

MATERIAL DATA SHEET

CoCr28Mo6

ASTM F75 / 2.4979

PRIME

Parameter Set	CoCr28Mo6_PRIM_MBP3_V1.0 (30 µm, 400 W)
Validated Data Preparation	Materialise SLM Build Processor
Theoretical Build Rate ⁴	11.0 cm ³ /h
Minimum Relative Density ⁵	99.9 %

Mechanical Properties⁶

M: Mean | SD: Standard deviation

Non-heat-treated (NHT)

Machined	Tensile strength R _m [MPa]		Yield strength R _{p0.2} [MPa]		Elongation at break A [%]	
	M	SD	M	SD	M	SD
Horizontal	1270	15	825	35	13	3
Vertical	1180	35	640	30	23	4

Hardness⁷

M: Mean | SD: Standard Deviation

NHT	Vickers hardness HV10	
	M	SD
	385	6

Surface Roughness⁸

M: Mean | SD: Standard Deviation

	Roughness average Ra [µm]		Mean roughness depth Rz [µm]	
	M	SD	M	SD
As built	16	3	99	13
Corundum	7	1	50	9
Corundum + Glass bead	6	1	41	4

MATERIAL DATA SHEET

CoCr28Mo6

ASTM F75 / 2.4979

PRODUCTIVITY

Parameter Set	CoCr28Mo6_PROD_MBP3_V1.0 (60 µm, 400 W)
Validated Data Preparation	Materialise SLM Build Processor
Theoretical Build Rate ⁴	19.5 cm ³ /h
Minimum Relative Density ⁵	99.8 %

Mechanical Properties⁶

M: Mean | SD: Standard deviation

Non-heat-treated (NHT)

Machined	Tensile strength R _m [MPa]		Yield strength R _{p0.2} [MPa]		Elongation at break A [%]	
	M	SD	M	SD	M	SD
Horizontal	1250	10	850	20	18	1
Vertical	1160	25	665	15	27	5

Hardness⁷

M: Mean | SD: Standard Deviation

NHT	Vickers hardness HV10	
	M	SD
	380	5

Surface Roughness⁸

M: Mean | SD: Standard Deviation

	Roughness average Ra [µm]		Mean roughness depth Rz [µm]	
	M	SD	M	SD
As built	15	4	91	17
Corundum	7	2	46	11
Corundum + Glass bead	6	1	41	4

MATERIAL DATA SHEET

CoCr28Mo6

ASTM F75 / 2.4979

DISCLAIMER

The properties and mechanical characteristics apply to powder that is tested and sold by SLM Solutions, and that has been processed on SLM Solutions machines using the original SLM Solutions parameters in compliance with the applicable operating instructions (including installation conditions and maintenance). The part properties are determined based on specified procedures. More details about the procedures used by SLM Solutions are available upon request.

The specifications correspond to the most recent knowledge and experience available to us at the time of publication and do not form a sufficient basis for component design on their own. Certain properties of products or parts or the suitability of products or parts for specific applications are not guaranteed. The manufacturer of the products or parts is responsible for the qualified verification of the properties and their suitability for specific applications. The manufacturer of the products or parts is responsible for protecting any third-party proprietary rights as well as existing laws and regulations.

© 2022 SLM Solutions. All rights reserved. Subject to change without notice.

MDS_CoCr28Mo6_2022-10.1_EN

CONTACT

Headquarters

SLM Solutions Group AG
Estlandring 4
23560 Lübeck
Germany

Phone: +49 451 4060-3000

www.slm-solutions.com



NOTES

- ¹ With respect to powder material. Compositions stated as mass or weight percent.
- ² Material density varies within the range of possible chemical composition variations.
- ³ According to DIN EN ISO 3252:2001.
- ⁴ Theoretical system build rate = layer thickness x scan speed x hatch distance x number of lasers. The value represents a comparable indicator but remains a theoretical value after all. It does expressively not reflect true build rates, which are influenced by part geometry, ratio between hatch and contour areas, area of exposure, recoating times, and more.
- ⁵ Optical density determination at test specimens by light microscopy according to internal specification. Relative density may vary depending on part geometry, orientation, volume, and other process factors.
- ⁶ Tensile testing was performed in accordance to DIN EN ISO 6892-1:2017 B and conducted at room temperature. Samples are either machined before testing or tested in near-net-shape without any surface finishing (geometry according to DIN 50125:2016-D6x30). Values include overlap samples, i.e. multiple lasers work simultaneously on one specimen. All data is derived from standardized SLM Solutions qualification jobs. Samples are built out of both virgin powder as well as used powder.
- ⁷ Hardness testing according to DIN EN ISO 6507-1:2018. Measurement direction "2" according to VDI 3405 2.1. Values include overlap samples, i.e. multiple lasers work simultaneously on one specimen. All data is derived from standardized SLM Solutions qualification jobs. Samples are built out of both virgin powder as well as used powder.
- ⁸ Roughness measurement on vertical walls according to DIN EN ISO 4288:1998; $\lambda_c = 2.5$ mm. Glass bead blasting is an additional post-processing step after corundum blasting. Values include overlap samples, i.e. multiple lasers work simultaneously on one specimen. All data is derived from standardized SLM Solutions qualification jobs. Samples are built out of both virgin powder as well as used powder.